



Steinzeugstraße 92, 68229 Mannheim Tel. +49 621 405 47 - 400 www.kyocera-solutions.de

## **MATERIAL DATA SHEET**

Material type: Aluminium Oxide (Al<sub>2</sub>O<sub>3</sub>)

## **DEGUSSIT AL25**

Properties		Unit	Specific value
Main component		-	$\alpha$ - $Al_2O_3$
Purity		wt%	> 99.5
Density		g / cm <sup>3</sup>	> 2.80
Open porosity		vol%	20 - 30
Average size of crystallites		μm	70
Bending strength $\sigma_{m}$	DIN EN 843-1	MPa	70
Compressive strength		MPa	300
Maximum service temperature in air		°C	1950
Coefficient of thermal expansion	20 - 1000°C	10 <sup>-6</sup> / K	8.2
Typical colour		-	white

The data indicated on this table are in line with the introductory German Industrial Standard DIN 60672-2 and relate to test specimens from which they are obtained. They are not unconditionally applicable to other forms of the same material. The data must be regarded as indicative only. All data refer to a temperature of 20 °C, unless otherwise specified.