

Material type: Mg-PSZ (magnesia partially stabilized zirconia)

FRIALIT FZM

Properties		Unit	Specific value
Main components		-	ZrO ₂ , MgO
Purity		wt-%	> 99.7
Density		g / cm ³	≥ 5.7
Open Porosity		vol.-%	0
Average Size of Crystallites		µm	50
Bending Strength σ_m	DIN EN 843-1	MPa	500
Weibulls Modulus		-	> 15
Toughness K_{Ic}	SEVNB	MPa * m ^{0.5}	6.3
Compressive Strength		MPa	2000
Young's Modulus	static	GPa	185
Poisson's Ratio		-	0.3
Hardness	Knoop, 100 g	GPa	16
Maximum Service Temperature in Air		°C	900
Linear Coefficient of Expansion	20 - 100 °C	10 ⁻⁶ / K	9.3
	20 - 500 °C	10 ⁻⁶ / K	10.4
	20 - 900 °C	10 ⁻⁶ / K	10.6
Specific Heat	20 °C	J / (kg * K)	400
Thermal conductivity	20 °C	W / (m * K)	3
	500 °C	W / (m * K)	2.3
	900 °C	W / (m * K)	2
Resistivity	20 °C	Ω * cm	10 ¹⁰
	900 °C	Ω * cm	84
Typical Colour		-	yellow

The data indicated on this table are in line with the introductory German Industrial Standard DIN 40680 and relate to test specimens from which they were obtained. They are not unconditionally applicable to other forms of the same material. The data must be regarded as indicative only. All data refer to a temperature of 20 °C, unless otherwise specified.

The material is extremely resistant to corrosion.

We should be pleased to send you brochures about the corrosion resistance of oxide ceramics.