

DEGUSSIT® ZR25

February 2025

Material Type: Fused stabilized zirconia ($\text{ZrO}_2 + \text{MgO}$)

MECHANICAL AND PHYSICAL PROPERTIES OF THE MATERIAL (TYP.)

Characteristic	Standard	Specification	Unit	Value
Content			[%]	> 99.0
Density (ρ_b)	DIN EN ISO 18754		[g/cm ³]	> 4.30
Open (apparent) porosity (π_a)	DIN EN ISO 18754		[vol-%]	~ 24
Flexural strength ($\sigma_{f,4}$)	DIN EN 843-1	Four-Point-Bending	[MPa]	80
Maximum service temperature ($T_{\max}$)		in air	[°C]	2200
Mean coefficient of linear thermal expansion ($\bar{\alpha}$)	DIN EN ISO 17562	20 - 500 °C	[10 ⁻⁶ /K]	7.2
		20 - 1000 °C		4.5
Specific heat capacity (c_p)	DIN EN 821-3	20 °C	[J/(kg·K)]	770
Thermal conductivity (λ)	DIN EN ISO 18755	30 °C	[W/m·K]	0.9
		1000 °C		1.9
Typical colour			[-]	sahara

The preliminary remark in DIN 60672-2 applies analogously to the property values given in the table, according to which the reported values apply only to the test specimens on which they were determined. Assignment to other forms is therefore only conditional permissible. The reference values given are to be understood as such. They refer to a temperature of 20 °C, unless otherwise stated.